

Component - Plastics

E189230

**BADA AG**

UNTERE STRUT 1, BUEHL/BADEN 77815 DE

**UL B70**

Polyamide 6 (PA6), "BADAMID", furnished as pellets

| Color | Min Thk<br>(mm) | Flame<br>Class | HWI | HAI | RTI<br>Elec | RTI<br>Imp | RTI<br>Str |
|-------|-----------------|----------------|-----|-----|-------------|------------|------------|
| ALL   | 0.8             | HB             | 4   | 0   | 65          | 65         | 65         |
|       | 1.6             | HB             | 4   | 0   | 65          | 65         | 65         |
|       | 3.0             | HB             | 3   | 0   | 65          | 65         | 65         |

Comparative Tracking Index (CTI): **0**

Inclined Plane Tracking (IPT): -

Dielectric Strength (kV/mm): -

Volume Resistivity (10<sup>x</sup> ohm-cm) : -High-Voltage Arc Tracking Rate  
(HVTR): **0**High Volt, Low Current Arc Resis (D495): **5**

Dimensional Stability (%): -

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 2001-09-22

Last Revised: 2011-11-25

© 2011 Underwriters Laboratories Inc.

**IEC and ISO Test Methods**

| Test Name                      | Test Method     | Units             | Thickness<br>Tested (mm) | Value      |
|--------------------------------|-----------------|-------------------|--------------------------|------------|
| Flammability                   | IEC 60695-11-10 | Class (color)     | 0.8                      | HB75 (ALL) |
|                                |                 |                   | 1.6                      | HB75 (ALL) |
|                                |                 |                   | 3.0                      | HB40 (ALL) |
| Glow-Wire Flammability (GWFI)  | IEC 60695-2-12  | C                 | -                        | -          |
| Glow-Wire Ignition (GWIT)      | IEC 60695-2-13  | C                 | -                        | -          |
| IEC Comparative Tracking Index | IEC 60112       | Volts (Max)       | -                        | -          |
| IEC Ball Pressure              | IEC 60695-10-2  | C                 | -                        | -          |
| ISO Heat Deflection (1.80 MPa) | ISO 75-2        | C                 | -                        | -          |
| ISO Tensile Strength           | ISO 527-2       | MPa               | -                        | -          |
| ISO Flexural Strength          | ISO 178         | MPa               | -                        | -          |
| ISO Tensile Impact             | ISO 8256        | kJ/m <sup>2</sup> | -                        | -          |
| ISO Izod Impact                | ISO 180         | kJ/m <sup>2</sup> | -                        | -          |
| ISO Charpy Impact              | ISO 179-2       | kJ/m <sup>2</sup> | -                        | -          |

© 2011 Underwriters Laboratories Inc.