



get the difference

BADAFLEX® | TPU 70A 8100 2K(PA) S1

TPU-I

Thermoplastic elastomer based on polyether; adhesion-modified injection moulding grade

Properties	Test conditions	Test method	Unit	dry as molded
Physical properties				
Hardness		DIN ISO 7619-1 DIN ISO 7619-1	Shore A Shore D	70 -
Density		ISO 1183	g/cm ³	1.09
Overmolding capability				PA6, PA66
Mechanical Properties				
Tensile Strength	Parallel, 200 mm/min Across, 200 mm/min	DIN 53504 DIN 53504	MPa MPa	35 35
Elongation at break	Parallel, 200 mm/min Across, 200 mm/min	DIN 53504 DIN 53504	% %	800 750
Tear Strength	Parallel Across	DIN ISO 34 DIN ISO 34	N/mm N/mm	45 -
Abrasion loss		DIN ISO 4649	mm ³	-
Thermal Properties				
Compression set	23 °C/72 h 70 °C/24 h 100 °C/24 h	DIN ISO 815-1 DIN ISO 815-1 DIN ISO 815-1	% % %	- - -
Thermal conductivity	Test plate 2 mm	DIN 52612-1	W/(m*K)	-
Flammability		UL94 UL94 UL94 UL94	Wall thickness Rating Wall thickness Rating	- - - -
Glow wire test GWIT		IEC-60695-2-13 IEC-60695-2-13 IEC-60695-2-13 IEC-60695-2-13	Wall thickness mm Temperature °C Wall thickness mm Temperature °C	- - - -
Glow wire test GWFI		IEC-60695-2-12 IEC-60695-2-12 IEC-60695-2-12 IEC-60695-2-12	Wall thickness mm Temperature °C Wall thickness mm Temperature °C	- - - -
Electrical Properties				
Spec. Volume Resistivity		IEC-62631-3-1	Ohm*cm	-
Spec. Surface Resistivity		IEC-62631-3-2	Ohm	-
Other Data				
Melt volume rate (MVR)	Value Temperature Test load	ISO 1133 ISO 1133 ISO 1133	cm ³ /10min °C kg	- - -
Processing injection molding				
Melt temperature			°C	200-240
Mold temperature			°C	60-80



get the difference

BADAFLEX® | TPU 70A 8100 2K(PA) S1

TPU-I

Thermoplastic elastomer based on polyether; adhesion-modified injection moulding grade

Properties	Test conditions	Test method	Unit	dry as molded
Guide Value Moisture			%	-
Drying temperature			°C	80-100
Guide Value Drying time			h	2-4

Issue date 07.03.2019

Legend

- = not tested
 NB = No break

Based on our current state of knowledge, this data represents reference values and, unless otherwise stated, stands for uncoloured material. Therefore, it does not constitute a warranty of certain properties, more particularly it is no material specification. It is the responsibility of the processors to check the suitability of the material for a particular application as well as compliance with statutory regulations and intellectual property rights. The data stated above may be modified at any time without prior notice. The information does not imply any contractual obligation on our part, any liability is expressly excluded.