



get the difference

BADAMID® | B70 GF50 H UV LB

PA6-GF50

50% glass fibres reinforced injection moulding grade with high strength, heat- and UV stabilized, suitable for laser marking

Properties	Test conditions	Test method	Unit	dry as molded	conditioned 23 °C, 50 % r.F.
Mechanical Properties					
Tensile Modulus	23°C, 1 mm/Min	ISO 527-1/2	MPa	15500	12100
Tensile Strength at yield	23°C, 50 mm/Min	ISO 527-1/2	MPa	-	-
Tensile strain at yield	23°C, 50 mm/Min	ISO 527-1/2	%	-	-
Nominal strain at yield	23°C, 50 mm/Min	ISO 527-1/2	%	-	-
Tensile stress at break	23°C, 5 mm/Min	ISO 527-1/2	MPa	230	160
Tensile strain at break	23°C, 5 mm/Min	ISO 527-1/2	%	3.0	5.0
Flexural Modulus	23°C	ISO 178	MPa	-	-
Flexural Strength	23°C	ISO 178	MPa	315	280
Charpy Impact Strength	23°C -30°C	ISO 179/1eU ISO 179/1eU	kJ/m ² kJ/m ²	100 95	110
Charpy Notched Impact Strength	23°C -30°C	ISO 179/1eA ISO 179/1eA	kJ/m ² kJ/m ²	21 21	26
Izod Notched Impact Strength	23°C -30°C	ISO 180/1A ISO 180/1A	kJ/m ² kJ/m ²	20 18	23
Ball indentation hardness	358 N	ISO 2039-1	MPa	-	-
Thermal Properties					
Melting temperature	10 K/min	ISO 3146	°C	222	
Temperature of deflection under load	0,45 MPa 1,8 MPa 8 MPa	ISO 75-1/2 ISO 75-1/2 ISO 75-1/2	°C °C °C	220 215 -	
Coefficient of linear thermal expansion	parallel across	ISO 11359-2 ISO 11359-2	E-4/K E-4/K	0.14 0.56	
Thermal conductivity	Test plate 2 mm	DIN 52612-1	W/(m*K)	-	
Maximum service temperature (50% decrease in tensile strength)	some hours 20.000 h	IEC-60216 IEC-60216	°C °C	200 110	
Flammability		UL94 UL94 UL94 UL94	Wall thickness mm Rating Wall thickness mm Rating	0.8 HB 1.6 HB	
Glow wire test GWIT		IEC-60695-2-13 IEC-60695-2-13 IEC-60695-2-13 IEC-60695-2-13	Wall thickness mm Temperature °C Wall thickness mm Temperature °C	- - - -	
Glow wire test GWF1		IEC-60695-2-12 IEC-60695-2-12 IEC-60695-2-12 IEC-60695-2-12	Wall thickness mm Temperature °C Wall thickness mm Temperature °C	- - - -	
Electrical Properties					
Relative Permittivity	1 MHz	IEC-62631-2-1	-	4.2	6.1
Dissipation Factor	1 MHz	IEC-62631-2-1	E-4	140	1400
Spec. Volume Resistivity	-	IEC-62631-3-1	Ohm*cm	1E15	1E12



get the difference

BADAMID® | B70 GF50 H UV LB

PA6-GF50

50% glass fibres reinforced injection moulding grade with high strength, heat- and UV stabilized, suitable for laser marking

Properties	Test conditions	Test method	Unit	dry as molded	conditioned 23 °C, 50 % r.F.
Spec. Surface Resistivity	-	IEC-62631-3-2	Ohm	1E13	1E10
Dielectric Strength	-	IEC-60243-1	kV/mm	-	-
Comparative Tracking Index (CTI)	-	IEC-60112	V	500	-
Other Data					
Water absorption	23°C, Saturation	ISO 62	%	4.8	
Moisture absorption	23°C, 50% r.h.	ISO 62	%	1.5	
Density	23°C	ISO 1183	g/cm ³	1.55	
Melt Volume Rate (MVR)	Value	ISO 1133	cm ³ /10min	-	
	Temperature	ISO 1133	°C	-	
	Test Load	ISO 1133	kg	-	
Viscosity number	0,5% in 96% H2SO4	ISO 307	cm ³ /g	-	
Processing injection molding					
Melt temperature			°C	270 - 300	
Mold temperature			°C	80 - 90	
Guide Value Moisture			%	< 0.15	
Drying temperature			°C	80	
Guide Value Drying time			h	2 - 4	

Issue date 22.02.2019

Legend

- = not tested
NB = No break

Based on our current state of knowledge, this data represents reference values and, unless otherwise stated, stands for uncoloured material. Therefore, it does not constitute a warranty of certain properties, more particularly it is no material specification. It is the responsibility of the processors to check the suitability of the material for a particular application as well as compliance with statutory regulations and intellectual property rights. The data stated above may be modified at any time without prior notice. The information does not imply any contractual obligation on our part, any liability is expressly excluded.