



*get the difference*

# BADAMID® | LC70 FR HF

PA66/6-FR

Co-Polyamide injection moulding grade, flame retardant without Halogens and without red Phosphorus; broad processing range

Properties	Test conditions	Test method	Unit	dry as molded	conditioned 23 °C, 50 % r.F.
<b>Mechanical Properties</b>					
Tensile Modulus	23°C, 1 mm/Min	ISO 527-1/2	MPa	3500	1500
Tensile Strength at yield	23°C, 50 mm/Min	ISO 527-1/2	MPa	85	45
Tensile strain at yield	23°C, 50 mm/Min	ISO 527-1/2	%	4	20
Nominal strain at yield	23°C, 50 mm/Min	ISO 527-1/2	%	6	>50
Tensile stress at break	23°C, 5 mm/Min	ISO 527-1/2	MPa	-	-
Tensile strain at break	23°C, 5 mm/Min	ISO 527-1/2	%	-	-
Flexural Modulus	23°C	ISO 178	MPa	-	-
Flexural Strength	23°C	ISO 178	MPa	-	-
Charpy Impact Strength	23°C -30°C	ISO 179/1eU ISO 179/1eU	kJ/m <sup>2</sup> kJ/m <sup>2</sup>	100 -	NB
Charpy Notched Impact Strength	23°C -30°C	ISO 179/1eA ISO 179/1eA	kJ/m <sup>2</sup> kJ/m <sup>2</sup>	6 4	35
Izod Notched Impact Strength	23°C -30°C	ISO 180/1A ISO 180/1A	kJ/m <sup>2</sup> kJ/m <sup>2</sup>	- -	-
Ball indentation hardness	358 N	ISO 2039-1	MPa	160	100
<b>Thermal Properties</b>					
Melting temperature	10 K/min	ISO 3146	°C	243	
Temperature of deflection under load	0,45 MPa 1,8 MPa 8 MPa	ISO 75-1/2 ISO 75-1/2 ISO 75-1/2	°C °C °C	210 70 -	
Coefficient of linear thermal expansion	parallel across	ISO 11359-2 ISO 11359-2	E-4/K E-4/K	0.68 0.81	
Thermal conductivity	Test plate 2 mm	DIN 52612-1	W/(m*K)	0.33	
Maximum service temperature (50% decrease in tensile strength)	some hours 20.000 h	IEC-60216 IEC-60216	°C °C	200 120	
Flammability		UL94 UL94 UL94 UL94	Wall thickness mm Rating Wall thickness mm Rating	0.4 V-0 3.0 V-0	
Glow wire test GWIT		IEC-60695-2-13 IEC-60695-2-13 IEC-60695-2-13 IEC-60695-2-13	Wall thickness mm Temperature °C Wall thickness mm Temperature °C	0.4 960 3.0 960	
Glow wire test GWF1		IEC-60695-2-12 IEC-60695-2-12 IEC-60695-2-12 IEC-60695-2-12	Wall thickness mm Temperature °C Wall thickness mm Temperature °C	0.4 960 3.0 960	
<b>Electrical Properties</b>					
Relative Permittivity	1 MHz	IEC-62631-2-1	-	3.6	6.0
Dissipation Factor	1 MHz	IEC-62631-2-1	E-4	200	3000
Spec. Volume Resistivity	-	IEC-62631-3-1	Ohm*cm	1E13	1E9



*get the difference*

# BADAMID® | LC70 FR HF

PA66/6-FR

Co-Polyamide injection moulding grade, flame retardant without Halogens and without red Phosphorus; broad processing range

Properties	Test conditions	Test method	Unit	dry as molded	conditioned 23 °C, 50 % r.F.
Spec. Surface Resistivity	-	IEC-62631-3-2	Ohm	-	1E12
Dielectric Strength	-	IEC-60243-1	kV/mm	32	28
Comparative Tracking Index (CTI)	-	IEC-60112	V	600	-
Other Data					
Water absorption	23°C, Saturation	ISO 62	%	8.5	
Moisture absorption	23°C, 50% r.h.	ISO 62	%	2.9	
Density	23°C	ISO 1183	g/cm <sup>3</sup>	1.16	
Melt Volume Rate (MVR)	Value Temperature Test Load	ISO 1133 ISO 1133 ISO 1133	cm <sup>3</sup> /10min °C kg	160 275 5	
Viscosity number	0,5% in 96% H2SO4	ISO 307	cm <sup>3</sup> /g	-	
Processing injection molding					
Melt temperature			°C	250 - 270	
Mold temperature			°C	60 - 80	
Guide Value Moisture			%	< 0.15	
Drying temperature			°C	80	
Guide Value Drying time			h	2 - 4	

Issue date 28.07.2021

**Legend**

- = not tested  
NB = No break

Based on our current state of knowledge, this data represents reference values and, unless otherwise stated, stands for uncoloured material. Therefore, it does not constitute a warranty of certain properties, more particularly it is no material specification. It is the responsibility of the processors to check the suitability of the material for a particular application as well as compliance with statutory regulations and intellectual property rights. The data stated above may be modified at any time without prior notice. The information does not imply any contractual obligation on our part, any liability is expressly excluded.